

TEST REPORT No. **101-1 SF/24 U**

page (pages)

Date: 09 of August 2024

1 (3)

**Determination of declared thermal resistance of reflective insulation product
according LST EN ISO 22097:2023, LST EN ISO 8990:1999 and product
technical specification LST EN 16863:2023**

	(test title)
Test method:	LST EN ISO 22097:2023 Thermal insulation for buildings - Reflective insulation products - Determination of thermal performance (ISO 22097:2023); LST EN ISO 8990:1999 Thermal insulation - Determination of steady-state thermal transmission properties - Calibrated and guarded hot box (ISO 8990:1994).
	(number of normative document or test method, description of test procedure, test uncertainty)
Specimen description:	Type of product: reflective insulation product (Type 3) Names of product: BOOST'R HYBRID / BOOST'R HYBRID ^S / BOOST'R HYBRID ^{MAX} Declared thickness – 8.5±1 cm* according EN 16863 (3 Pa) *according to the manufacturer declaration: report ACTIS 220210-declared thickness EN 823 (3 Pa)
	(name, description and identification details of a specimen)
Customer:	SA Orion financement – Avenue de la Gare – FR-11230 CHALABRE, France
	(name and address)
Manufacturer:	ACTIS SA : 30 Avenue de Catalogne - 11300 LIMOUX, France
	(name and address)

Test results:

Name of the indicator and unit	Test method reference no.	Test result
Declared core thermal resistance of product BOOST'R HYBRID $R_{D(core)90/90}$, (m²·K)/W	LST EN ISO 22097:2023	3.20
Declared thermal resistance of system with 2 air gaps $R_{system\ 90/90}$, (m²·K)/W		3.95
Declared thermal resistance values determined according to LST EN 16863:2023 Position of specimen: vertical (direction of heat flow – horizontal)		

Tested at: Building Physics Laboratory, Institute of Architecture and Construction of Kaunas University of Technology
(name of the test laboratory)



Specimen delivery date: 2024-03-18 – 2024-04-05 **Date of testing:** 2024-03-29 – 2024-04-13

Production date: 2023-11-27 – 2024-03-06

Sampling: The test specimens sampled by customer. Description of the sample 2023-11-22

Additional information: This report is prepared according to tests reports 088 002-1 SF/24 U; 088 003-1 SF/24 U; 101 004-1 SF/24 U; 101 005-1 SF/24 U.
(any deviations, complementary tests, exceptions and any information related with particular test)

Annexes: **Annex 1.** Parameters of Guarded Hot Box measurement;
Annex 2. Specimen air gaps thermal properties;
Annex 3. $R_{D(core)90/90}$ thermal resistance values according to LST EN 16863:2023.
(indicate annex numbers and titles)

Head of Laboratory: (approves the test results)	 (signature)	K. Banionis (n., surname)
Tested by: (technically responsible for testing)	 (signature)	A. Burlingis (n., surname)

Validity – the named data and results refer exclusively to the tested and described specimens.
Notes on publication – no part of this document may be photocopied, reproduced or translated to another language without the prior written consent of the Building Physics Laboratory.

Annex 1. Parameters of Guarded Hot Box measurement.

Table 1. The insulation system's specimen measured at 20°C / 0°C temperature regime

Guarded Hot Box measurement. Parameters of insulation system's specimen:						
Specimen's area A, m ²		1.831	Actual mean thickness of specimen, mm			≈ 149*
Position of a specimen		vertical	Length of specimen perimeter L, m			5.44
		Linear thermal transmittance of perimeter zone Ψ _L , W/(m·K)				0.004025
Measurement data:						
Insulation system with product:						Result:
Sample No.	Hot side surface temperature τ _h , °C	Cold side surface temperature τ _c , °C	Temperature difference Δτ = (τ _h - τ _c), °C	Measured heat flow density q, W/m ²	Corrected heat flow density q _c , W/m ²	R-value of insulation system, m ² ·K/W
088 002/24	20,2020	0,1093	20,0928	5,0951	4,8550	4,139±0,2035
088 003/24	20,2145	0,0903	20,1243	5,0424	4,8020	4,191±0,2060
101 004/24	20,1130	0,1013	20,0118	5,1108	4,8717	4,108±0,2020
101 005/24	20,0913	0,0923	19,9990	5,1305	4,8915	4,088±0,2011
Average:						4.1315

* Previous test has shown that when installed on real building the average thickness of product is slightly larger than its nominal value. To keep surfaces of test sample as parallel as possible in the test setup, it is decided to install the product in a frame. After internal validation, the thickness of the frame is representative of the average thickness of an installed product, as requested by LST EN ISO 8990.

$$S_{R\text{ system}} = \sqrt{\frac{\sum (R_i - R_{\text{average}})^2}{n - 1}};$$

$$S_{R\text{ system}} = 0.04487;$$

$$R_{\text{system } 90/90} = R_{\text{average}} - k_2 \cdot S_{R\text{ system}}; \quad n = 4; \quad k_2 = 3.19;$$

Thermal resistance of the core together with the thermal resistances of the unventilated vertical air spaces, rounded downwards to the nearest 0.05 m²·K/W:

$$R_{\text{system } 90/90} = 3.9884 = 3.95 \text{ m}^2 \cdot \text{K/W}$$

Annex 2. Specimen air gaps thermal properties

Table 2. The insulation specimen products

Specimen product	Specimen surface layer	Test method reference No.	Declared emissivity, ε
BOOST'R HYBRID	PERFORATED EXTER ALU	EN 22097:2023	0.08*
	HPV MEMBRANE		0.94**

*according to the manufacturer declaration – rapport 18/03/05 – Emissivite EN16012.

**according to the manufacturer declaration ACTIS 220309 – Emissivity EN 16012.

Validity – the named data and results refer exclusively to the tested and described specimens.
Notes on publication – no part of this document may be photocopied, reproduced or translated to another language without the prior written consent of the Building Physics Laboratory.

Table 3. The insulation specimen air gaps corrected R-core values calculation results according to LST EN 22097:2023 and LST EN ISO 6946:2017

Sample No.	Air gap number	Thickness d, mm	Measured temperature differences of surfaces, $\Delta\tau$, °C	Radiative heat transfer coefficient, h_r	Convective heat transfer coefficient, h_a	Air gap R (core) value, $m^2 \cdot K/W$
088 002/24	Air gap #1	30	2.451	0.4483	1.25	0.5888
	Air gap #2	30	1.299	3.9668	1.25	0.1917
088 003/24	Air gap #1	30	2.421	0.4485	1.25	0.5888
	Air gap #2	30	1.230	3.9645	1.25	0.1918
101 004/24	Air gap #1	30	2.369	0.4481	1.25	0.5889
	Air gap #2	30	1.245	3.9653	1.25	0.1917
101 005/24	Air gap #1	30	2.365	0.4480	1.25	0.5889
	Air gap #2	30	1.243	3.9649	1.25	0.1918

Annex 3. $R_{D(core)90/90}$ thermal resistance values according to LST EN 16863:2023

Table 4. R-core thermal resistance value according to LST EN 22097:2023

Sample No.	R(core) thermal resistance value according to LST EN 22097:2023
088 002/24	3.358 $m^2 \cdot K/W$
088 003/24	3.410 $m^2 \cdot K/W$
101 004/24	3.327 $m^2 \cdot K/W$
101 005/24	3.308 $m^2 \cdot K/W$
Average: 3.3508 $m^2 \cdot K/W$	

Standard deviation of derived R-value of insulation product:

$$S_{R(core)} = \sqrt{\frac{\sum (R_i - R_{average})^2}{n - 1}};$$

$$S_{R(core)} = 0.04455;$$

Declared core thermal resistance $R_{D(core) 90/90}$:

$$R_{D(core) 90/90} = R_{average} - k_2 \cdot S_{R system}; \quad n = 4; \quad k_2 = 3.19;$$

Thermal resistance of the core rounded downwards to the nearest 0.05 $m^2 \cdot K/W$ (LST EN 16863:2023):

$$R_{D(core) 90/90} = 3.2086 = 3.20 \text{ } m^2 \cdot K/W$$

Validity – the named data and results refer exclusively to the tested and described specimens.
Notes on publication – no part of this document may be photocopied, reproduced or translated to another language without the prior written consent of the Building Physics Laboratory.